

XOANONS® Polyether modified silicon leveling agent

Model number

XOANONS®WE-D5450

Specification

Composition	Polyether modified polydimethyl siloxane
Appearance	slight yellowish clear liquid(paste at low temperature)
Solvent	---
Density	1.01-1.05g/ml(25±1)°C
Viscosity	200-1000 mPa·s (Rotating viscometer)(25±0.2)°C
Active substance	100%
Flash point	>100°C

Note: This datasheet is intended to give typical results, not standard.
Subject to COA.

Application system

Water-based, Solvent-based, UV Cure

Properties

- Provide a stronger reduction of the surface tension.
- Reduce the friction coefficient. Increase slip and improve scratch resistance.
- Good recoating and minimal influence on adhesion of coating films.
- Good property of anti-crater.
- Hazy and viscous may occur at low temperatures. It would become clear and flow after heated. This will not influence the quality.

Incorporation

Easy to add with pre-diluted solvent the same as that in the coating system. Can added as post-addition.

Suggest addition

Addition to total formulation 0.01-0.5%

Storage stability

Keep intact 24 months in original package. Products beyond the storage period may continue to be used after inspection. The container must be closed immediately after use.

Applicate recommendation

Transparency in varnish	5
Defoaming	0
Dynamic surface tension	5
Static surface tension	5
Slip	4
Prevent orange peel	1

0=unavailable 5=very effective

Package

25KG / 180KG